



RAINBOW

RED LEAD PRIMER, GENERAL PURPOSE

NO.	No.911
TYPE	Anti-corrosive paint based on alkyd and special resins with high red lead content.
USES	Anti-corrosive under coat for topsides, steel decks, superstructures and weathering steel parts
CHARACTERISTICS	<ol style="list-style-type: none">1. Fast drying with good adhesion.2. Good resistance to seawater and oil.3. Very good rust preventive properties.4. Reality low cost.
COLOR	Orange
GLOSS	Flat
HIDING POWER	Above 9.1 m ² /L
WEIGHT	Above 1.55 Kg/L
VISCOSITY (25 °C)	75 - 95 KU (25°C)
DRYING TIME (25 °C)	Set-to-touch 1/2 hr. Dry hard 4 hrs.
OPTIMUM FILM THICKNESS	Wet 90 microns Dry 40 microns
THEORETICAL COVERAGE	42.0 m ² /Gal 11.0 m ² /L 7.0 m ² /kg
OVERCOATING INTERVALS (25°C)	Min. 6 hrs. Max. 3 months
NON-VOLATILE CONTENT	Above 70%
THINNER	No.805 Thinner
THINNING RATE	5~20% (Use for cleaning tools is not included)
PRECEDING COATS	No.908
SUBSEQUENT COATS	Synthetic Enamel, Ready-Mixed Paint
STORAGE SHELF LIFE	Minimum 1 year under normal storage condition.
APPLICATION METHODS	Brush, Roller or Air spray
NOTES	<ol style="list-style-type: none">1. Paint has to be stirred consistently. If it is too thick, thinner can be added according to regulated quantity.2. Moisture, grease, rust, loose film and corrosive contaminant have to be removed form applied surface and be cleaned up completely.3. Application should not be proceeded under cloudily day and upon damp surface neither under the environment when temperature higher than 40 °C or lower than 10°C.4. Subsequent coat can be applied only when preceding coat is completely ure.

YUNG CHI PAINT & VARNISH MFG.CO.,LTD

26. YEN HAI 3RD ROAD. KAOHSIUNG, TAIWAN

TEL : 886-7-8713181 FAX : 886-7-8715443