



RAINBOW

ENAMEL TOPSIDE (SILVER)

PRODUCT NUMBER	SP-76
TYPE	Topside paint based on alkyd and special resins with aluminum pigment.
USES	Topcoat for cargo holds.
CHARACTERISTICS	<ol style="list-style-type: none">1. Tough film with good abrasion resistance.2. Good humidity resistance.3. Good resistance to oil and water.4. Good adhesion.5. Easy application.
FINISH	Gloss
COLOR	Silver
FLASH POINT	Above 25°C (77°F)
SPECIFIC GRAVITY	Above 0.9 Kg/L
VISCOSITY	50 ~ 70 KU (25°C)
DRYING TIME	Set-to-touch 1 hr. Dry hard 3 hrs. (25°C)
OPTIMUM FILM THICKNESS	Wet 65 microns (2.6 mil) Dry 25 microns (1.0 mil)
THEORETICAL COVERAGE	58.3 m ² /Gal 15.4 m ² /L 17.1 m ² /Kg
OVERCOATING INTERVALS	Min. 6 hrs. (25°C)
VOLUME SOLIDS	Above 39 %
THINNER	No.805 Paint Thinner (OM-07)
THINNING RATE	5~10 % (cleaning tools excluded)
PRECEDING COATS	SP-54 High Red Lead Primer (OP-91) SP-56 Red Oxide Primer (OP-95) No.920 LZI Primer (OP-94)
STORAGE SHELF LIFE	Minimum 1 year under normal storage conditions.
APPLICATION METHOD	Airless Spray, Brush, Roller
FOR AIRLESS SPRAY	Tip Size Graco 621, 721 Air Pressure 3~5 Kg/cm ² Pump Ratio 45 : 1 or 33 : 1

YUNG CHI PAINT & VARNISH MFG.CO.,LTD

26. YEN HAI 3RD ROAD. KAOHSIUNG, TAIWAN

TEL : 886-7-8713181 FAX : 886-7-8715443