



RAINBOW

VINYL RED LEAD PRIMER

PRODUCT NUMBER	SP-30 (VP-71)
TYPE	Anti-corrosive paint based on vinyl resin and red lead pigment.
USES	Anti-corrosive primer for topside area, deck fittings and superstructures.
CHARACTERISTICS	<ol style="list-style-type: none">1. Very fast drying.2. Very good resistance to sea water and oil.3. Tough and flexible.4. Excellent adhesion to vinyl topcoats.
FINISH	Semi-gloss
COLOR	Orange
FLASH POINT	Above 8°C (46°F)
SPECIFIC GRAVITY	Above 1.1 Kg/L
VISCOSITY	70 ~ 90 KU (25°C)
DRYING TIME	Set-to-touch 1/2 hr. Dry hard 2 hrs. (25°C)
OPTIMUM FILM THICKNESS	Wet 120 microns (4.8 mil) Dry 30 microns (1.2 mil)
THEORETICAL COVERAGE	31.4 m ² /Gal 8.3 m ² /L 7.5 m ² /Kg
OVERCOATING INTERVALS	Min. 3 hrs. (25°C)
VOLUME SOLIDS	Above 25 %
THINNER	SP-36 Vinyl Thinner (VF-61)
THINNING RATE	5~10 % (cleaning tools excluded)
PRECEDING COATS	No.908 Wash Primer (SP-01/02) No.1006 Epoxy Zinc Primer (EP-03) Epoxy primers
STORAGE SHELF LIFE	Minimum 1 year under normal storage conditions.
APPLICATION METHOD	Airless Spray
NOTE	<ol style="list-style-type: none">1. Application of vinyl paints should not be done in damp foggy or rainy weather and the relative humidity should never exceed 85%.2. Before applying vinyl A/C, steel surface must be thoroughly cleaned, and coated with one coat of wash primer.3. For discriminating the number of coatings, tinting with vinyl color enamel is recommended.

YUNG CHI PAINT & VARNISH MFG.CO.,LTD

26. YEN HAI 3RD ROAD. KAOHSIUNG, TAIWAN

TEL: 886-7-8713181 FAX: 886-7-8715443